


IN THE CLAIMS

17. The method of manufacturing the fluorocarbon-based polymer coating film according to claim 12, wherein the compound comprising a fluorocarbon group and an alkoxysilyl group is represented by:



where n represents 0 or an integer;

R represents an alkylene group or a hydrocarbon substituted group containing C=C or C≡C, a silicon atom or an oxygen atom;

m represents 0 or 1;

Y represents a hydrogen atom, an alkyl group, an alkoxy group, a fluorine-containing alkoxy group or a fluorine-containing alkyl group;

OA' represents an alkoxy group; and

q' represents 0, 1 or 2;

and the method further comprises a step of baking the substrate after coating.

21. A method of producing a fluorocarbon-based coating film on a glass substrate comprising:

depositing a siloxane-based inner layer on a surface of the glass; and

coating the siloxane-based inner layer with a compound comprising (1) a fluorocarbon group and a chlorosilyl group or (2) a fluorocarbon group and an alkoxysilyl group.

31. A production method of an apparatus comprising a part comprising a fluorocarbon-based polymer coating film comprising:

a. contacting the part having a surface containing hydroxyl groups with a non-aqueous solvent comprising a material comprising chlorosilyl groups to form a siloxane-based film on the apparatus surface; and

b. coating the siloxane-based film with a non-aqueous solvent comprising a compound comprising a fluorocarbon group and a chlorosilyl group, represented by the formula: $\text{CF}_3-(\text{CF}_2)_n-(\text{R})_m-\text{SiX}_p\text{Cl}_{3-p}$ where n represents 0 or an integer; R represents an alkylene group or a hydrocarbon substituted group containing $\text{C}=\text{C}$ or $\text{C}\equiv\text{C}$, a silicon atom or an oxygen atom; m represents 0 or 1, X represents a hydrogen atom or an alkoxy group; p represents 0, 1 or 2.

32. A production method of claim 31, wherein said material comprising chlorosilyl groups is selected from the group consisting of SiCl_4 , SiHCl_3 , SiH_2Cl_2 and $\text{Cl}-(\text{SiCl}_2\text{O})_n-\text{SiCl}_3$, wherein n is an integer.

33. A production method of claim 31, wherein p represents 0.

34. A production method of claim 31, wherein the apparatus is an electric apparatus, a vehicle or an industrial apparatus.

35. A apparatus made by the method of claim 34.

36. The method of claim 27, wherein the vehicle part is made of the member of a group consisting of glass, metals, plastics and ceramics.

37. The method of claim 31, wherein the part is selected from the group consisting of glass, metals, plastics and ceramics.

38. A method of manufacturing a vehicle part comprising:
forming a siloxane-based film on the vehicle part surface; and

coating the siloxane-based film with a non-aqueous solvent comprising a compound comprising a fluorocarbon group and a chlorosilyl group.

39. The method of claim 38, wherein the siloxane-based film is made with a material comprising chlorosilyl groups selected from the group consisting of SiCl_4 , SiHCl_3 , SiH_2Cl_2 and $\text{Cl}-(\text{SiC}_2\text{O})_n-\text{SiCl}_3$, wherein n is an integer.

40. The method of claim 38, wherein the vehicle part is a window glass of a vehicle.

41. A production method of an apparatus having a part applied with a fluorocarbon-based polymer coating film comprising:

forming a siloxane-based film on the part surface; and

coating the siloxane-based film with a non-aqueous solvent comprising a compound comprising a fluorocarbon group and a chlorosilyl group.

42. The method of claim 41, wherein the siloxane-based film is made with a material comprising chlorosilyl groups selected from the group consisting of SiCl_4 , SiHCl_3 , SiH_2Cl_2 and $\text{Cl}-(\text{SiC}_2\text{O})_n-\text{SiCl}_3$, wherein n is an integer.

43. The production method of claim 41, wherein the apparatus is an electric apparatus, a vehicle or an industrial apparatus.

44. An apparatus made by the method of claim 43.

45. The apparatus of claim 44, wherein the apparatus is a vehicle.